


Investigation of aluminahydrate as a fire retardant in silica filled rubber floor-tiles.

A research project thesis submitted in partial fulfillment of the degree of Master of Science in Polymer Technology.

By
Kamal Asoka Rajapaksha.



56 "04"
678(043)

Polymer Technology Division,
Department of Chemical Engineering,
University of Moratuwa,
Sri Lanka.

September 2004.

University of Moratuwa



82709

Thesis

82709

82709



DECLARATION

I hereby declare that this submission is a result of a work carried out by me and to the best of my knowledge. It contains no material previously written or published by another person nor material which has been accepted for the award of any degree or acceptable qualification of a University, or other institute of higher learning, except where the reference to the material is made.

UOM Verified Signature

.....

K.A.Rajapaksha
September 2004.



University of Moratuwa, Sri Lanka.
Electronic Theses & Dissertations
www.lib.mrt.ac.lk

ACKNOWLEDGEMENT

I am grateful to my supervisors Mr. K. Subramaniam (MSc course co-ordinator, senior lecturer, department of Chemical Engineering) and Mr. Shanthi koratota (Operational Director Kinetics (Pvt) Ltd. Biyagama) for their guidance, patience shown throughout the project.

My especial thanks to Mr. Shanthi koratota, for supporting me by providing all the required materials and facilities.

I would like to thank all the divisional managers and executives and laboratory staff of my firm, kinetics (Pvt) Ltd, Biyagama for their great support given to me in all my experimental works.

My special thanks are due to the factory manager and other staff of Arpitalian Compact Soles (Pvt) Ltd, Biyagama, for their assistance in offering some test results of my experimental works.

I would also like to thank all the library members of ITI (former CISIR) for providing me the required facilities with out any restriction.

Finally my thanks are due to my parents, family members, and my friends for their fullest support given me to preparation of this thesis.

ABSTRACT

The flame-retardant chemicals, which commercially find applications in rubbers, are considered to be toxic chemicals, because of the liberation of their harmful volatile by products, when rubbers are on fire.

From the research works in the recent past it has been established that the chemical, aluminahydrate is one of the safest and environmentally friendly flame retardants. As a result, the application of this chemical as a flame-retardant in rubbers and plastics is on the rise, at present particularly in the developed western countries.

Thus in view of utilizing this chemical in local industries, as a flame retardant especially in the silica filler added rubber floor - tile compounds, an attempt has been made in this work, to evaluate the chemical for its fire retardant property in their vulcanizates.



University of Moratuwa, Sri Lanka
Electronic Theses & Dissertations
www.lib.mrt.ac.lk

The study reveals that to obtain optimum flame retardance in the rubber floor tiles, the conventional rubber compounds containing 40 phr precipitated silica should be incorporated with atleast 105 phr of aluminahydrate in place of 5 phr of the mixture of chlorinated paraffin wax and antimony trioxide.

TABLE OF CONTENTS

	Page No
Declaration	ii
Acknowledgement	iii
Abstract	iv
Table of Contents	v
List of figures	Vii
List of tables	Viii

Chapter 1 - Introduction.

1.1	Flame spreading in rubber and preventing fire retardants	2
1.2	Aim of the project	9
1.3	Method of approach	9
1.4	Historical review of prevention of fire	10
1.5	The present situation of fire and its prevention	12



Electronic Theses & Dissertations
www.lib.mrt.ac.lk

Chapter 2 - Experimental.

2.1	Material chosen	14
2.2	Preparation of rubber compounds	20
2.3	Processability tests	22
2.4	Physical testing of vulcanizates	22
	2.4.1 Tensile properties	23
	2.4.2 Hardness	25
	2.4.3 Abrasion resistance	25
2.5	Methods of testing flame retardant property of aluminahydrate added rubber vulcanizates.	27
	2.5.1 Combustibility test inclined at 45 ⁰ angle position	27
	2.5.2 Combustibility test – in vertical position	29
	2.5.3 Combustibility test - in horizontal position	30
	2.5.4 Smoke measurement test	31

Chapter 3 – Test results – Tables

3.1	Test results of processability characteristic	35
3.2 to 3.3	Test results of physical test of vulcanizates	36
3.4 to 3.6	Test results of combustibility	38
3.7	Assessment test results of smoke density	41
3.8	Classes obtained from test results	42
3.9	ASTM Standard buildings	43

Test results – Graphs

3.1	Graph of Rheometer characteristics	34
3.2	Graph of processability characteristic	44
3.3 – 3.4	Graphs of physical test of vulcanizates	45
3.5 – 3.7	Graphs of combustibility	47
3.8	Graph of smoke density	50



of Moratuwa, Sri Lanka.
Electronic Theses & Dissertations
www.lib.mrt.ac.lk

Chapter 4 - Results and discussion.

4.1	Results and Discussion.	52
4.2	Conclusion	59
4.3	Further work to be done	60
4.4	Appendix 1, 11, 111	61
4.5	References	67

LIST OF FIGURES

Page No.

Figure 2.1	Sketch for Gotech testing Machines Inc.-Rheometer tester	22
Figure 2.2	Sketch for Tensile strength test pieces.	24
Figure 2.3	Durometer- Rubber hardness tester.	25
Figure 2.4	DIN abrader-Rubber abrasion resistance tester.	26
Figure 2.5	The test apparatus for combustible tests-sample positioned 45°.	28
Figure 2.6	The test apparatus for combustible tests-in vertical position.	29
Figure 2.7	Determination of rate of burning horizontal- Left: Front view, Right: side view	30
Figure 2.8	Arapahoe smoke box test apparatus	31
Figure 3.1	Rheometer graph	34
Figure 3.2a	Teste results-tensile strength	44
Figure 3.2b	Test results-modulus at 300% elongation	44
Figure 3.2c	Test results-elongation at break	44
Figure 3.3	Hardness test results	45
Figure 3.4	Abrasion resistance test results	46
Figure 3.5	Results of combustibility test-45° angle	47
Figure 3.6	Results of combustibility test -vertical positon	48
Figure 3.7	Results of combustibility test -horizontal positon	49
Figure 3.8	Results of smoke density	50
Figure 4.1a,b	comparision of ts2 and t90 with working limit for different formulations	54, 55
Figure 4.1c,d	comparision of ML and MH with working limit for different formulations	55, 56

List of Tables

		Page No.
Table 1.1	Estimated consumption of fire retardants in the USA in year 2000.	12
Table 2.1	Formulations for rubber compounds.	21
Table 3.1	Results of tensile strength ,modulus at 300% and elongation	35
Table 3.2	Hardness test results	36
Table 3.3	Abrasion resistance test results	37
Table 3.4	Results of combustibility tests - 45 ⁰ position	38
Table 3.5	Results of combustibility tests - vertical position	39
Table 3.6	Results of combustibility tests - horizontal position	40
Table 3.7	Results of smoke density	41
Table 3.8	Classes obtained from the test results	42
Table 3.9	ASTM standard building codes	43
Table 4.1	working limits of processing characterristics	52
Table 4.2	Standard values of physical characteristics required for floor tiles	52
Table 4.3	Standard and modified rubber floor tile formulations	53
Table 4.4	Rheometer data for prepared rubber compound mix	54